Anima Wonder

TECHNICAL DATA

DECO-TILE

· Tile Performance Data ·

· Classification in accordance with EN ISO 14411 ISO 13006 annex G standards Bla with Ev ≤ 0,5%

	TILE PERFORMANCE DATA	TESTS METHOD	LUCIDATO GL
	Size	ISO 10545-2	In accordancet
	Water absorption*	ISO 10545-3	≤ 0,1%
	Bending strength*	ISO 10545-4	In accordance
	Breaking strength	ISO 10545-4	Sps ≥ 7,5 mm S ≥ 1300 N
	Impact resistance	ISO 10545-5	≥ 0,80
	Deep scratch resistance*	ISO 10545-6	-
	Thermal linear expansion coefficient*	ISO 10545-8	≃ 7 (10^{-6} °C-1)
	Thermal shock resistance*	ISO 10545-9	Resistant
	Expansion in humidity*	ISO 10545-10	In accordance
	Crazing resistance	ISO 10545-11	In accordance
	Frost resistance*	ISO 10545-12	Resistant
	Resistance to chemical attack●	ISO 10545-13	Resistant
	Resistance to stains*	ISO 10545-14	Cleanable
	Slip resistance**	DIN 51130 - DIN 51097 ▲ ANSI A326.3	- -
	Surface abrasion resistance	EN ISO 10545-7	Tests available at our company
	Mohs hardness	EN 101	Coeff. 5
	Nominal Thickness		6 mm 120x278, 60x120 9 mm 120x120, 60x120

* Averege values referred to the lasto two years of production.

** As far as values relating to the matt finish of the product and to tests carried out by certified external laboratories whose results are avaible upon request at Headoffice, we are willing to check the lot you are interested in purchasing.

● For domestic chemicals and swimming pool additives.

▲ Wet DCOF specific values available at the company.

DECO-TILE

STAY CONNECTED
-
www.decotile.com
@decotile

Locations

Toronto
Head Office + Warehouse

143 Tycos Dr.
Toronto, ON M6B 1W6
416 413 7985

Oakville
Showroom

550 Speers Rd. Unit #2
Oakville, ON L6K 2G3
905 582 7985