Prima

TECHNICAL DATA

DECO-TILE

TILE PERFORMANCE DATA

Classification in accordance with EN ISO 14411 ISO 13006 annex G standards Bla with Ev ≤ 0,5%

	TILE PERFORMANCE DATA	TESTS METHOD	MATT / SOFT	AEXTRA20		
	Size	ISO 10545-2	In accordance	In accordance		
	Water absorption*	ISO 10545-3	≤ 0,1%	≤ 0,1%		
	Bending strength*	ISO 10545-4	In accordance	Not applicable to tiles with a breaking strenght		≥ 3000 N
	Breaking strength	ISO 10545-4	Sps ≥ 7,5 mm S ≥ 1300 N	> 10.000 N		
	Deep scratch resistance*	ISO 10545-6	In accordance	In accordance		
	Thermal linear expansion coefficient*	ISO 10545-8	≃ 7 (10^{-6} °C^{-1})	≃ 7 (10^{-6} °C-1)		
	Thermal shock resistance*	ISO 10545-9	Resistant	Resistant		
	Expansion in humidity*	ISO 10545-10	≤ 0,1 (mm/m)	≤ 0,1 (mm/m)		
	Frost resistance*	ISO 10545-12	Resistant	Resistant		
	Resistance to chemical attack•	ISO 10545-13	Resistant	Cleanable		
	Static load	EN 12825	-		60x60	80x80
				Centre	KN>7,0	KN>3,0
				Side centre	KN>5,0	KN>3,0
				Diagonal	KN>8,0	KN>6,5
	Breaking load class***	EN 1339	-	U11 ***		
				T11 ***		
	Resistance to stains*	ISO 10545-14	Cleanable	Cleanable		
	Slip resistance**	DIN 51130 DIN 51097	R9 Matt 120x278	R10 B Matt 60x120 - 80x80 - 60x60 - 30x60	Soft -	R11 C
		ANSI A326.3	WET DCOF ≥0,42			WET DCOF ≥0,55
	Nominal Thickness		6 mm 120x278			20 mm 80x80 - 60x60
			9 mm 120x120 - 60x120 - 80x80 - 60x60 - 30x60			

* Averege values referred to the lasto two years of production.

** As far as values relating to the matt finish of the product and to tests carried out by certified external laboratories whose results are avaible upon request at Headoffice, we are willing to check the lot you are interested in purchasing.

*** Detail referred to the 60x60 cm size.

• For domestic chemicals and swimming pool additives.

PRIMA

DECO-TILE

DECO-TILE

STAY CONNECTED
-
www.decotile.com
@decotile

Locations

Toronto
Head Office + Warehouse

143 Tycos Dr.
Toronto, ON M6B 1W6
416 413 7985

Oakville
Showroom

550 Speers Rd. Unit #2
Oakville, ON L6K 2G3
905 582 7985