Travertino

TECHNICAL DATA

DECO-TILE

	PORCELAINED STONEWARE WITH MASS COLOURING		CLASS		CE Bla GL
Symbolics	Features	Unit of mesurement	mean value	Fixed value	Test method
	Side straightness	%	Nat. +/- 0,5 Rett. +/- 0,3	Nat. +/- 0,5 max Rett. +/- 0,3 max	UNI EN ISO 10545-2
	Corner squaraness	%	Nat. +/- 0,5 Rett. +/- 0,3	Nat. +/- 0,5 max Rett. +/- 0,3 max	UNI EN ISO 10545-2
	Flatness	%	+/- 0,4	+/- 0,5 max	UNI EN ISO 10545-2
	Thickness	%	+/- 5,0	+/- 5,0 max	UNI EN ISO 10545-2
	Water absorption	%	< 0,2	≤ 0,5	UNI EN ISO 10545-3
	Breaking strenght	N	≥ 1600 se Spess. ≥ 7,5 ≥ 700 se Spess. ≤ 7,5	≥ 1300 se Spess. ≥ 7,5 ≥ 700 se Spess. ≤ 7,5	UNI EN ISO 10545-4
	Modulus of rupture	N/mm²	> 40	≥ 35	UNI EN ISO 10545-4
	Coeff. of linear thermal expansion	°MK (-1)	7,0	available method	UNI EN ISO 10545-8
	Thermal shock resistyance	-	resist	available method	UNI EN ISO 10545-9
	Stain resistance	-	≥ 3	3 MIN	UNI EN ISO 10545-14
	Resistance to chemical products	-	conform	MIN GB	UNI EN ISO 10545-13
	Resistant to acids and low concentration bases	-	MIN GLB	according to product classification	UNI EN ISO 10545-13
	Frost resistance	-	resist	request	UNI EN ISO 10545-12
	Colour stability	-	stable	available method	DIN 51094

DECO-TILE

DECO-TILE

STAY CONNECTED
-
www.decotile.com
@decotile

Locations

Toronto
Head Office + Warehouse

143 Tycos Dr.
Toronto, ON M6B 1W6
416 413 7985

Oakville
Showroom

550 Speers Rd. Unit #2
Oakville, ON L6K 2G3
905 582 7985