

GLACIER

TECHNICAL DATA

DECO-TILE



Floor: Glacier Cream 120x120

Formatos / Sizes / Formats

280x120 Rec. 110"x48" ± 6 mm	6	120x120 Rec. 48"x48" ± 10,2 mm	7	60x120 Rec. 24"x48" ± 10,5 mm	14
------------------------------------	---	--------------------------------------	---	-------------------------------------	----

Glacier

POLISHED GLAZED PORCELAIN TILES



Glacier White

PEI 4



Glacier Cream

PEI 4

Formato s Sizes Formats	pz/cj pc s/bx pz/bt	m²/cj m²/bx m²/bt	cj/pal bx/pal bt/pal	m²/pal m²/pal m²/pal	kg/cj kg/bx kg/bt	kg/pal kg/pal kg/pal
280x120	1	3.36	20	67.20	52.00	1,140.00
60x120	2	1.44	32	46.08	34.25	1,121.00
120x120	1	1.44	36	51.84	34.36	1,276.96

TEST			VALUE
	UNE-EN ISO 10545-2	DIMENSIONAL CHARACTERISTICS	SATISFIES THE NORM
	UNE-EN ISO 10545-3	WATER ABSORPTION	$\leq 0,5 \%$
 N/mm ²	UNE-EN ISO 10545-4	FLEXURAL STRENGTH - BREAKING STRENGTH	1600-2400 N
		FLEXURAL STRENGTH - MODULUS OF RUPTURE	35-45 N/mm ²
	UNE-EN ISO 10545-6	RESISTANCE TO DEEP ABRASION (MM ³)	NOT APPLICABLE
	UNE-EN ISO 10545-7	RESISTANCE TO SURFACE ABRASION	-
	UNE-EN ISO 10545-8	LINEAR THERMAL EXPANSION	$<7,0 \times 10^{-6} \text{ }^{\circ}\text{C}^{-1}$
	UNE-EN ISO 10545-9	RESISTANCE TO THERMAL SHOCK	RESISTS
	UNE-EN ISO 10545-11	RESISTANCE TO CRAZING	RESISTS
	UNE-EN ISO 10545-12	RESISTANCE TO FROST	RESISTS
	UNE-EN ISO 10545-13	CHEMICAL RESISTANCE - AMMONIUM CHLORIDE 100 G/L	A
		CHEMICAL RESISTANCE - SODIUM HYPOCHLORITE 20 MG/L	A
		CHEMICAL RESISTANCE - HYDROCHLORIC ACID 3%	SATISFIES THE NORM
		CHEMICAL RESISTANCE - CITRIC ACID 100 G/L	SATISFIES THE NORM
		CHEMICAL RESISTANCE - POTASSIUM HYDROXIDE 30 G/L	SATISFIES THE NORM
	UNE-EN ISO 10545-14	STAIN RESISTANCE - GREEN AGENT IN LIGHT OIL	5
		STAIN RESISTANCE - IODINE SOLUTION IN ALCOHOL	5
		STAIN RESISTANCE - OLIVE OIL	5



STAY CONNECTED

-

www.decotile.com
@decotile

Locations

Toronto
Head Office + Warehouse
143 Tycos Dr.
Toronto, ON M6B 1W6
416 413 7985

Oakville
Showroom
550 Speers Rd. Unit #2
Oakville, ON L6K 2G3
905 582 7985